



KÖSTER Restoration Plaster White/Light

White, light weight restoration plaster for salt- and moisture damaged masonry for hand or spray application

Features

KÖSTER Restoration Plaster White/Light is a fast setting, salt and pressure resistant restoration plaster for the restoration of heavily moisture and salt burdened substrates. Due to its high porosity and hydrophobicity, KÖSTER Restoration Plaster White/Light allows for the damage free drying and de-salting of masonry even in the case of high salt contents. It improves the insulative properties of the wall and therefore helps prevent the formation of condensate. KÖSTER Restoration Plaster White/Light is free of light fillers and therefore requires no further surface treatment prior to the application of breathable paints or wallpaper which is open to vapor diffusion.

Technical Data

Porosity of fresh mortar	> 30 V-%
Porosity of cured plaster	> 40 V-%
Compressive strength (28 days)	5.0 N / mm ²
Flexural tensile strength (28 days)	2 N / mm ²
Modulus of Elasticity	> 5500 N / mm ²
Setting time	approx. 2 hours
Working time (23 °C, 65 % RH)	approx. 60 minutes
Minimum application temperature	+ 5 °C
Water consumption per 20 kg bag	5.0 - 5.5 l

Fields of Application

KÖSTER Restoration Plaster White/Light is suitable for the repair of moisture and salt damaged masonry, also after the post installation of a horizontal barrier with KÖSTER Crisin 76, KÖSTER Mautrol, KÖSTER Mautrol 2C, or KÖSTER Mautrol Flex 2C. It can be applied to reduce the formation of condensate after waterproofing rooms with high humidity using mineral sealing slurries such as the KÖSTER KD System or KÖSTER NB 1 Grey. KÖSTER Restoration Plaster White/Light can also be used as a decorative water repellent exterior plaster. In the case of exterior application we recommend the application of KÖSTER Repair Mortar on the base area up to 30 cm above ground level.

Substrate

Suitable substrates include concrete, masonry consisting of brick, natural stone, porous concrete block, perforated brick, mixed masonry, etc., sealing slurries such as KÖSTER NB 1 Grey, KÖSTER NB 2 White, or the KÖSTER KD System. Prior to the application of KÖSTER Restoration Plaster White/Light, the substrate is primed with KÖSTER Polysil TG 500 with a minimum consumption of 120 g / m². Apply the KÖSTER Polysil TG 500 until the surface is saturated. In the case of strongly absorbent substrates the consumption can be up to 250 g / m². KÖSTER Polysil TG 500 should be applied to a substrate previously treated with KÖSTER NB Waterproofing Slurry after 48 hours at the earliest. Loose particles and salt efflorescence should be removed mechanically prior to the beginning of the restoration. Substrates containing gypsum are not suitable substrates and the gypsum must be removed.

Application

KÖSTER Restoration Plaster Key

A plaster key is a thin slurry which is used as a bonding bridge between the substrate and the Restoration Plaster. The KÖSTER Restoration Plaster Key is cast onto the substrate with a brush or a trowel (Consumption approx. 4-6 kg / m²) so that the plaster key is no thicker than 5 mm and covers approximately 50% of the area. After hardening (approx. after 30 to 60 minutes) the Restoration Plaster can be applied.

The key can also be made of KÖSTER Restoration Plaster Grey with the addition of max. 10% KÖSTER SB bonding emulsion added to the mixing water (Consumption approx. 3 kg / m²). The Key Course is cast onto the substrate with a brush or a trowel so that the plaster key is no thicker than 5 mm and covers approximately 50% of the area, (Consumption approx. 2.5 - 3.0 kg / m²). After hardening the KÖSTER Restoration Plaster White/Light can be applied.

Mix each 20 kg bag of KÖSTER Restoration Plaster White/Light with 5.0 - 5.5 l of fresh water. The plaster is usually applied in two coats with a total layer thickness of approx. 2.5 cm. The layer thickness should be at least 2 cm. and maximum 3 cm. For layers thicker than 2.5 cm, it is recommended to apply in two layers. The second layer is applied within 24 hours or after 28 days. After casting the plaster onto the substrate, it is trued using a feather edge, a straight edge, or a long float trowel. Once the plaster starts to set it is smoothed using a float. Do not use a felt or sponge float to smooth the surface. Do not re-wet the surface after the initial floating. If several layers of plaster are to be applied, the lower layer is roughened thoroughly by scratching immediately after it begins to set. Interior surfaces can be smoothed using KÖSTER Fine Plaster. KÖSTER Fine Plaster must be applied either within 3 days after the application of the last coat of KÖSTER Restoration Plaster White/Light or after the restoration plaster has cured for 28 days.

Machine processing

For plastering machines, the water adjustment values must be set in such a way that a consistent consistency is achieved. The settings to be selected depend on the machine, the type of rotor, and the wear of the stator.

Suitable plastering machines are, for example, the PFT G4 or G5 with Rotoquirl after-mixer, Putzknecht S 48.3 or S 58 each with after-mixer R 3 , > stockbig No.1-400 with after-mixer or comparable machine types from other manufacturers. Rotor / stator must be with air inlet.

Repair against capillary rising moisture

Immediately following the closure of the drill holes with KÖSTER KB-Fix 5, the salt treatment and substrate consolidation can be carried out with KÖSTER Polysil TG 500, (minimum consumption 120 g / m², for strongly absorbent substrates up to 250 g / m²). Immediately afterwards, a key coat made from KÖSTER Restoration Plaster white / light and KÖSTER SB Bonding Emulsion (diluted 1: 3 with water) can be applied, (consumption: approx. 2.5 - 3.0 kg / m²), after another 24

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

