



KÖSTER TPO 1.5

EPD-KBC-20160014-IBC1-DE Environmental Product Declaration according to the ISO 14025 and EN 15804

Official Test Report according to 1200/057/15 DIN EN 13956 MPA Braunschweig, Official Test Report according to 5278/015/14 DIN EN 13967 MPA Braunschweig, Certificate of conformity of the factory production control 0761-CPR-0422 MPA Braunschweig, Fish test A14-02548 BMG Zürich, Official Test Report according to ETAG 006 4/2015 I.F.I. Aachen

TPO Roofing and Waterproofing membrane with central glass fleece insert

Grey

Keißeres Round Corner Patch light grey

KÖSTER TPO Metal Composite Coil grey Prod. code RT 910 030

KÖSTER TPO Metal Composite Sheet

Features

- Plastic waterproofing membrane made of high quality thermoplastic polyolefins based on polyethylene (PE)

- central glass fleece insert
- uniform material quality (no difference between upper and lower side)
- homogeneous seam bonding with hot air welding
- temperature and weather resistant
- aging and rot resistant
- high cold flexibility (\leq -50 °C)
- UV-stable
- root resistant
- compatible with bitumen
- compatible with polystyrene
- suitable for all types of insulation
- resistant against normal mechanical stresses
- resistant to microorganisms and rodent attack
- environmentally friendly
- free of softeners and chlorine
- safe for health, water, soil, and plants
- recyclable

Technical Data

Refer to last page

Fields of Application

KÖSTER TPO Roofing and Waterproofing Membranes are used to waterproof unventilated and ventilated flat roofs, pitched roofs, green roofs, terraces, balconies, roof gardens and underground garages with ballast and in cases of direct exposure to weathering. KÖSTER TPO Roofing and Waterproofing Membranes can be used for the waterproofing of basements, wet rooms and tanks.

Application

Please refer to the TPO Installation Instructions and the Technical Manual for TPO of KÖSTER BAUCHEMIE AG for correct application of KÖSTER TPO Roofing and Waterproofing Membranes.

Packaging			
RT 815 025	1.5 mm x 0.25 m x 20 m		
RT 815 035	1.5 mm x 0.35 m x 20 m		
RT 815 052	1.5 mm x 0.525 m x 20 m		
RT 815 075	1.5 mm x 0.75 m x 20 m		
RT 815 105	1.5 mm x 1.05 m x 20 m		
RT 815 150	1.5 mm x 1.50 m x 20 m		
Related products			
KÖSTER Contact Adhesive	Prod. code RT 102		
KÖSTER TPO 2.0 U	Prod. code RT 820 U		
KÖSTER External Corner light grey	/ 90 Prod. code RT 901 001		
degrees			
KÖSTER Internal Corner light grey	90 Prod. code RT 902 001		

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu

Technical Data Sheet RT 815

Prod. code RT 903 001

Prod. code RT 910 002

Issued: 2019-10-07



	KÖSTER BAUCHEMIE AG	
	Dieselstraße 1-10, 26607 Aurich	
		R TPO 1.5
	EN 13956 0761-CPR-0422	
0761	EN 13967 0761-CPR-0423	
15	TPO (PE) roofing and waterproofing membrane with	
	central glass fleece insert	
Length according to DIN EN 1848-2	20 m ¹⁾	
Width according to DIN EN 1848-2	2.10; 1.50; 1.05; 0.75; 0.525; 0.35; 0.25 m	
Effective thickness according to DIN EN 1849-2	1.5 mm	
	DIN EN 13956: 2012 waterproofing of flat and sloped roofs. Application by loose laying with ballast or mechanical fastening	DIN EN 13967:2012 Vapor Barrier Type T
Designation according DIN SPEC 20000-201 and DIN SPEC 20000-202	DE/E1-FPO-BV-E-GV-1,5	BA-FPO-BV-E-GV-1,5
Color	Standard: light grey ²⁾	light grey
Visible Defects according to DIN EN 1850-2	free from visible defects	free from visible defects
Straightness according to DIN EN 1848-2	$\leq 50 \text{ mm}$	\leq 50 mm
Flatness according to DIN EN 1848-2	≤ 10 mm	
Mass per unit area according to DIN EN 1849-2	1490 g /m ²	1490 g /m²
Water tightness according to DIN EN 1928 (Method B)	400 kPa/24h watertight	400 kPa/72h watertight
Exposure to liquid chemicals, including water according to	passed (Method B)	watertight (Method A)
DIN EN 1847		water light (methou A)
Exposure to external fire according to DIN CEN/TS 1187; DIN 4102-7; DIN EN 13501-5	Broof(t1) ³⁾	-
Reaction to fire according to EN 13501-1	Class E	Class E
Resistance to hail according to DIN EN 13583	Class E	Class E
Rigid substrate	≥ 25 m/s	
Soft substrate	$\geq 38 \text{ m/s}$	-
Peel resistance of the overlap according to	\geq 500 N/50 mm	
DIN EN 12316-2	≥ 500 W/50 mm	-
Shear resistance of the overlap according to DIN EN	Failure beyond the overlap	Failure beyond the overlap
12317-2	Failure beyond the overlap	Fallure beyond the overlap
Water vapor diffusion resistance according to DIN EN 1931	μ = 85,000	μ = 85,000
Tensile characterisitcs according to DIN EN 12311-2		
Tensile strength	\geq 7 N/mm ² (Method B)	\geq 7 N/mm ² (Method B)
Elongation at break	≥ 500 % (Method B)	≥ 500 % (Method B)
Resistance to shock loads according to DIN EN 12691	> E00 mm	> 500 mm
Method A	≥ 500 mm	≥ 500 mm
Method B	≥ 1000 mm	≥ 1000 mm
Resistance to static loading according to DIN EN 12730	> 00 km	> 00 km
Method A	≥ 20 kg	≥ 20 kg
Method B	≥ 20 kg	≥ 20 kg
Tear continuation resistance according to DIN EN 12310-2	≥ 200 N	≥ 200 N
Root penetration resistance ⁴⁾	given	-
Dimensional stability according to DIN EN 1107-2	≤ 0.2 %	≤ 0.2 %
Folding at low temperatures	≤ - 50°C	-
according to DIN EN 495-5	pagaad: Lavel 0	
Behavior under UV irradiation, elevated temperatures, and	passed: Level 0	-
water according to DIN EN 1297 (1000 h)	pagaad	
Ozone resistance according to DIN EN 1844	passed	- watertight
Exposure to bitumen according to DIN EN 1548	passed	watertight
Durability against heat storage	watertight	watertight
according to DIN EN 1296, DIN EN 1928 (Method A)	> 500 N	> 500 N
Tear resistance (nail shank) according to DIN EN 12310-1 1) Special lengths available on request 2) Other colors available or	\geq 500 N	≥ 500 N

1) Special lengths available on request 2) Other colors available on request 3) Requirements are met for roofs tested by KÖSTER in Germany. Further information can be requested from KÖSTER. 4) Applies only to green roofs

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu

R - Roofing membranes, roof waterproofing